

1.5# Black Beaded EPE

Typical Physical Properties:

Specification	Test Method	Typical Results
Density	ASTM D3575	1.5 lbs/ft ³ ± 0.25
Compression Strength @ 25% @ 50% @ 75%	ASTM D3575	11 psi 19 psi 49 psi
Tensile Strength	ASTM D3575	45 psi
Tensile Elongation	ASTM D3575	30%
Tear Strength	ASTM D3575	16 lbs/in
Compression Set @ 25% @ 50%	ASTM D3575	4% 13%
Buoyancy	ASTM D3575	59.5 lbs/ft ³
Thermal Conductivity	ASTM C177	0.24 BTU-in /ft ² -hr-°F
Thermal Resistance	ASTM C177	4.2 (R) @ 70°F
Service Temperature	ASTM D3575	160°F
Water Absorption	ASTM D3575	~1.0%
Compression Creep	ASTM D3575	3.0 , 1000 hrs @ 1 psi
Flammability	FMVSS 302	Pass
Chemical Resistance	Various 1 hour exposure	Pass
Fuel Immersion	Coast Guard (CGD-770145) Fuel B	Pass

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warrant, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that is accurate to the best of MILCUT INC. knowledge or obtained from sources believed by MILCUT INC. to be accurate, and MILCUT INC. does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.