

1.7# White EPE

Typical Physical Properties

Physical Property	Test Method	Typical Results
Density Range	ASTM D3575-00	1.4-1.8 lbs/ft ³
Compressive Strength @ 25% @ 50%	ASTM D3575-00, Suffix D	6 psi 14.5 psi
Compression Set	ASTM D3575-00, Suffix B	21%
Compression Creep	ASTM D3575-00, Suffix BB 168 hrs.	<10% @ 1.25 psi
Tensile Strength <i>MD</i> <i>CMD</i>	ASTM D3575-00, Suffix T	35 psi 24 psi
Tear Resistance <i>MD</i> <i>CMD</i>	ASTM D3575-00, Suffix G	11 lbs/in 8 lbs/in
Cell Size	ASTM D3576 Modified	1.2 mm
Water Absorption	ASTM D3575-00, Suffix L	<0.1 lbs/ft ²
Thermal Stability	ASTM D3575-00, Suffix S	<5%
Contact Corrosivity (Alum. Plate)	Method 3005, FED STD. 101	None
Static Decay	EIA STD. 541, Appendix F	<2 sec
Surface Resistivity	EIA STD. 541, Section 4.3	1.0 x 10 ⁹ -1.0 x 10 ¹²
Thermal Conductivity	ASTM C518-91	0.34-0.43 BTU-in/hr-ft ² -°F
Thermal Resistance	ASTM C518-91	2.38-2.94 hr-ft ² -°F/BTU

Variety of densities and colors available.

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warrant, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that is accurate to the best of MILCUT INC. knowledge or obtained from sources believed by MILCUT INC. to be accurate, and MILCUT INC. does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.