

## 2# UL Ester

### Typical Physical Properties

Physical Property	Typical Results
Pore Size	60-80 PPI
Density	1.75-2.10 lbs/ft <sup>3</sup>
Tensile Strength	15.0 psi min
Elongation	175% min
Tear Strength	1.5 lbs/in min
CFD 25%R(2"x2"x1")	0.40 psi min
CFD 65%R(2"x2"x1")	0.70 psi min
Compression Set, 50%	15% max
Flammability	
<i>UL94 HF-1</i>	Pass
<i>FMVSS 302</i>	Pass
Clickability	Pass

**Meets MIL-PRF-26514G, Type 1, Class 2, Grade C**

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warrant, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that is accurate to the best of MILCUT, INC. knowledge or obtained from sources believed by MILCUT, INC. to be accurate, and MILCUT, INC. does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.