

## 60 PPI Green Filter Foam

### Typical Physical Properties

Specification	Test Method	Typical Results
Pore Count	Pressure Drop	60-70 PPI
Density	ASTM D3574	1.70-2.00 lbs/ft <sup>3</sup>
Tensile Strength	ASTM D3574	22.0 psi
Elongation	ASTM D3574	200% min.
Tear Strength	ASTM D3574	3.5 lbs/in
CFD 25% R(2"x2"x1")	ASTM D3574	0.30 psi
CFD 65% R(2"x2"x1")	ASTM D3574	0.50 psi
Compression Set 50%	ASTM D3574M	30% max.
Clickability		Pass

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warrant, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that is accurate to the best of MILCUT INC. knowledge or obtained from sources believed by MILCUT INC. to be accurate, and MILCUT INC. does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.