



Constantly seeking better ways to be the best®

Black Pyramid Matting

Typical Physical Properties

Physical Property	Test Method	Typical Results
Durometer, Shore A	ASTM D2240	80 ± 5
Tensile Strength	ASTM D412	600 psi
Elongation	ASTM D412	150%
Tear Resistance, Die C	ASTM D412	100 lbf/in
Surface Finish		Pyramid
Back Finish		Textured Cloth Impression
Color		Black
Flammability	FMVSS 302	Pass

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warrant, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that is accurate to the best of MILCUT INC. knowledge or obtained from sources believed by MILCUT INC. to be accurate, and MILCUT INC. does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.