

Black Pyramid Matting

Typical Physical Properties

Specification	Test Method	Typical Results
Specific Gravity	ASTM D792	1.45-1.55
Durometer	ASTM D2240	75-85
Tensile Strength	ASTM D412, Die C	800 psi
Elongation	ASTM D412, Die C	200%
Flammability	FMVSS 302	Pass

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warrant, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that is accurate to the best of MILCUT INC. knowledge or obtained from sources believed by MILCUT INC. to be accurate, and MILCUT INC. does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.