

Black TPE

Typical Physical Properties

Physical Property	Test Method	Typical Results
Hardness	ASTM D2240	81
Density	ASTM D279	1.05 g/cm ³
Tensile Strength <i>Along Grain</i> <i>Across Grain</i>	ASTM D412, Die C	6.0 Mpa 5.6 Mpa
Elongation <i>Along Grain</i> <i>Across Grain</i>	ASTM D412, Die C	240% 226%
Tear Strength <i>Along Grain</i> <i>Across Grain</i>	ASTM D624, Die B	30 kN/m 36 kN/m
Low Temperature	ASTM D2137, Method A -40°C for 3 min.	Pass No Cracks
Heat Aging <i>Tensile Strength Change</i> <i>Elongation Change</i> <i>Hardness Change</i> <i>Tackiness Change</i>	ASTM D573 70 hrs @ 70°C	4% -9% -1 OK, No Cracks
Compression Set	ASTM D395, Method B Except 25% Comp. Plied 22 hrs @ 70°C	42%

Meets the requirements of WSS-M2D492-A1
Meets WSS-M99P9999-A1

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warrant, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that is accurate to the best of MILCUT INC. knowledge or obtained from sources believed by MILCUT INC. to be accurate, and MILCUT INC. does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.