



Constantly seeking better ways to be the best®

## Kydex® Plastic

### Typical Physical Properties

Specification	Test Method	Typical Results
Specific Gravity	ASTM D792	1.35
Tensile Strength	ASTM D638	6,100 psi
Elongation	ASTM D638	110%
Flexural Strength	ASTM D790	9,600 psi
Modulus of Elasticity	ASTM D790	360,000 psi
Notched Izod Impact Resistance, @ 73°F	ASTM D256	15 ft-lbs/in
Heat Deflection Temperature @ 264 psi annealed	ASTM D648	168°F
Flammability	UL Standard 94	V-0, 5V
Federal Aviation Administration	FAR 25.853 (a)	Pass

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warrant, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that is accurate to the best of MILCUT INC. knowledge or obtained from sources believed by MILCUT INC. to be accurate, and MILCUT INC. does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.