

## 1.8# Low Permeability Polyether Foam

### Typical Physical Properties

Specification	Minimum	Maximum	Units
Pore Size	26	40	PPI
Density	1.81	2.50	lbs/ft <sup>3</sup>
Tensile Strength	9.0		psi
Elongation	125		%
Tear Strength	1.0		lbs/in
CLD 25%R(2"x2"x1")	0.10		psi
Compression Set 50%		15	%
Pressure Pot	1.0		psi
Flammability MVSS 302	Pass		
Operating Temperature	-40°F	200°F	
Intermittent Temperature		250°F	

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warrant, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that is accurate to the best of MILCUT INC. knowledge or obtained from sources believed by MILCUT INC. to be accurate, and MILCUT INC. does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.