



Constantly seeking better ways to be the best®

Melamine

Description:

This is a low density, high temperature foam material which minimizes the problems of toxicity, carcinogens and airborne fibers. It is highly fire resistant, with a service temperature between -150°F up to +356°F, and has low smoke generation, produces low out gassing and has outstanding thermal and acoustical properties.

Typical Physical Properties

Physical Property	Typical Results
Density	0.7 lbs./ft ³
Elongation	10%
Compression Set:	
@ 50%	6.2%
@ 75%	8.5%
@ 90%	14.4%
Indentation Force Deflection	
@ 25%	82 lbs./ft
@ 75%	356 lbs./ft
Heat Conductivity (K factor)	0.25 at 68°F
Ozone/UV Resistance	Resistant to ozone but should not be exposed to strong UV radiation
Chemical Resistance	Resistant to organic solvents and various diluted acids and alkali
Flammability (2" thick sample)	
FMVSS 302 (Automotive)	Pass
UL-94 (Electronics)	HBF, HF1, V-O: Pass
FAR 25.853 (Aviation)	Pass
ASTM E-84 Steiner Tunnel Test	Flame Spread: 2.5 Smoke Density: 16.9

Chemical Resistance

Solvent/Chemical	Type	Typical Results
Distilled Water		0
Bases	Sodium Hydroxide (50%) Ammonia (25%)	0 -
Acids	Hydrochloric acid (10%) Conc. Hydrochloric acid (38%) Nitric acid (10%) Sulfuric acid (10%) Conc. Sulfuric acid (10%) Phosphoric acid (50%) Acetic acid (90%) Formic acid (90%) Lactic acid (5%) Citric acid (5%)	- - - - - - 0 0 0 -
Salt Solutions	Sea water (NaCl-sol. 3.6%)	0
Hydrocarbons	Light Petrol (60 to 140°C) Heavy Petrol (155 to 185°C) Paraffin Oil Methylene Chloride Toluene	+ + + + +
Alcohols	Methanol Ethanol Isopropanol Butanol Glykolmonoethylether Glycerin	+ + + + + +
Esters	Butyacetat	+
Ketone	Acetone	+
Other Solvents	Diethylether	+

+: Resistant

0: Limited Resistance

-: Not Resistant

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warrant, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that is accurate to the best of MILCUT INC. knowledge or obtained from sources believed by MILCUT INC. to be accurate, and MILCUT INC. does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.