

Neoprene/EPDM/SBR Blend

Typical Physical Properties

Specification	Typical Results
Color	Black
Specification	
<i>ASTM D1056-00</i>	2A5
<i>ASTM D1056-67</i>	SCE 45
<i>SAE J18-02</i>	2A5
<i>GM 6086M</i>	IIIB
<i>GMN11106</i>	IIIB
25% Compression Deflection	17-24 psi
Shore 00 Durometer (approx.)	65+
Density	12-20 lbs/ft ³
Water Absorption by Weight	5%
Temperature Range	-70° to 225°F
Weather Resistance	
<i>UV</i>	Fair
<i>Ozone</i>	Good
Accelerated Linear Shrinkage	5%
Tensile Strength	90 psi
Elongation	100%
Flammability (FMVSS 302)	Pass

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warrant, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that is accurate to the best of MILCUT INC. knowledge or obtained from sources believed by MILCUT INC. to be accurate, and MILCUT INC. does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.