



Constantly seeking better ways to be the best®

14% Black Perforated Vinyl On 1.9# Ether

Typical Physical Properties for 1.9# Ether

Specification	Minimum Results	Typical Results
Density	1.90 lbs/ft ³ ± 10%	1.90 lbs/ft ³ ± 10%
Tensile Strength	20.0 psi	25.0 psi
Elongation	180%	300%
Tear Resistance	1.50 lbs/in	3.00 lbs/in
Indentation Force Deflection 25% Deflection 65% Deflection	30 lbs/50 in ² 55 lbs/50 in ²	40 lbs/50 in ² 80 lbs/50 in ²
Retention of Tensile Strength After 5 hrs, 120°C, Steam autoclave After 22 hrs, 140°C, dry heat aging	Min. 70% Min. 70%	Min. 70% Min. 70%
Air Flow	0.50 ft ³ /4 in ² /min	0.50 ft ³ /4 in ² /min
Flammability <i>FMVSS 302</i>	Meets	Meets

Typical Physical Properties for Perforated Vinyl

Specification	Test Method	Typical Results
Thickness	ASTM D751	0.55 mm ± 10%
Width	ASTM D751	57 in
Weight	ASTM D751	23 oz ± 2.0
Coating Adhesion, MD/CD	ASTM D751	3.0 lbs/3.0 lbs min
Tensile Strength, MD/CD	ASTM D751	35 lbs/35 lbs min
Tear Strength, MD/CD	ASTM D5587	5.5 lbs/5.5 lbs min
Cold Crack	FED 191A-5874	-20°F
UV Resistance	ASTM G53	500 hours gray scale 3.5 min
Flammability	FMVSS 302	Pass
Abrasion (Wyzenbeek)	ASTM D4157	50,000 cycles

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warrant, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that is accurate to the best of MILCUT INC. knowledge or obtained from sources believed by MILCUT INC. to be accurate, and MILCUT INC. does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.