



Constantly seeking better ways to be the best®

Thermal & Acoustical Shield

Description:

This material is a shield that serves as an advanced alternative to traditional thermal and acoustical metal shields. It is comprised of high-performance aluminum sheeting, a mechanically needle-punched fiber composite spacer, and a unique, high-temperature pressure-sensitive adhesive on the back for attachment to low surface energy composites and CARC paint. It can be used in a variety of applications such as underbody above exhaust system, HVAC thermal protection, fuel tank thermal protection and underhood component protection.

Advantages:

- Acoustical sound deadening benefits
- Withstands 246°C (475°F) oven test for 30 hours with no failure
- IR signature masking

Typical Physical Properties

Physical Property	Test Method	Typical Results	Pass/Fail
Material Type		Polyester needled composite with laminated aluminum foil and PSA	
Core Thickness		6.4 mm ± 2 mm	
Foil Thickness		.25mm	
Moisture Absorption	WSS-M99P32-D6, Sect. 3.7.6	0.2%	PASS
Thermal Conductivity, (k-Value)	ASTM C518	25°C: 0.036 W/m/°K 45°C: 0.038 W/m/°K 65°C: 0.040 W/m/°K	PASS
Tensile Strength	ASTM D5034	MD: 439 N/cm ² CD: 522 N/cm ²	PASS
Tear Resistance	ISO 9073-4	MD: 785 N CD: 444 N	PASS
Peel Adhesion <i>HDPE</i> <i>PP</i> <i>SMC</i>	ASTM D3330, Method F 24 hr dwell @ 21°C & 50% RH	16.3 N/cm 14.8 N/cm 14.3 N/cm	PASS

THE VALUES PRESENTED ARE TYPICAL AND ARE NOT INTENDED FOR SPECIFICATION PURPOSES. This information is provided without warrant, representation, inducement or license of any kind. INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR USE OR PURPOSE, except that is accurate to the best of MILCUT INC. knowledge or obtained from sources believed by MILCUT INC. to be accurate, and MILCUT INC. does not assume any legal responsibility for the use or reliance upon same. Customers are encouraged to conduct their own tests for suitability and conformance.